

Product Data Sheet:

GacoFlex™ GacoPatch Compliant
August 2019

GACOFLEX™ GACOPATCH COMPLIANT LOW VOC SILICONE ROOF PATCH

DESCRIPTION:

GacoFlex GacoPatch Compliant is a low VOC, flashing grade, standalone silicone roof patch designed to be installed in a single application without reinforcement on a variety of substrates. GacoPatch Compliant is specially formulated for regions requiring a VOC content less than 50 g/L. In most cases, GacoPatch Compliant may be installed in a one-step application, reducing labor time and eliminating the cost of additional products such as primers and top coats.

New and improved technology allows for GacoPatch Compliant to be a long term repair solution. GacoPatch Compliant does not contain asphalts or acrylics, and is extremely durable. GacoPatch Compliant remains permanently flexible, even under ponding water, and is UV stable, so it will not chalk or crack.

Fabric reinforcement may be added as desired at angle changes, or when flashing irregularly shaped penetrations. Sacrificial tape is recommended when repairing cracks more than 1/8" in diameter and all cracks that are subject to movement.

USAGE:

Use GacoPatch Compliant on surface cracks*, control joints*, coping joints*, gutter seams, membrane pinholes, rain collars and fish mouths*, or as pitch pan filler.

^{*}May require the use of sacrificial tape.

PRODUCT DATA	
Color	GP1500C White, GP1525C Gray*, GP1573C Black* *Do not use colored silicones over asphaltic substrates.
Consistency	Thick, caulk-like material.

APPLIED PRODUCT DATA		
Weatherability	Excellent color retention and excellent resistance to UV degradation.	
Chemical Resistance	Excellent chemical resistance.	
Hardness (GP1500C)	ASTM D2240 55 Shore A	
Adhesion	Bonds to most aged asphalt membranes*, including APP, SBS, Smooth Built-Up and Mineral Surface Cap Sheets, aged Single Ply Membranes, Concrete, Sprayed Polyurethane Foam, and most existing coatings. Adhesion tests are recommended; prime where necessary. ** Adhesion to all Metal substrates and new TPO or PVC requires the use of a primer. Existing silicone coatings should not be primed. *Discoloration or blistering may occur over some asphaltic substrates. **Follow S20/S21 primer recommendations on General Instructions GW-4-1 Primer Guide.	
Toxicity	Not suitable for contact with edible substances or potable water storage systems.	

PACKAGED PRODUCT DATA		
Coverage	7.8 Gal per 100 ft² (29.5 L per 9.3 m²) when applied at 125 wet mils: 1.8" (45.7 mm) thick NOTE: Application rate is job-specific. Additional material may be required.	
Solids (GP1500C)	METHOD 4041 Weight: 96% Volume: 94.40%	
Tensile Strength (GP1500C)	ASTM D412 Strength: 145 psi Elongation: 63%	
Tear Resistance (GP1500C)	ASTM D624 DIE C 19 lb/in	
V.O.C.	< 50 g/L (< 0.417 lb/gal)	
Flash Point	ASTM D3278 178 °F (81 °C)	
Storage Stability	Two years from date of manufacture when stored in original, unopened container between $0 ^{\circ}\text{F} - 75 ^{\circ}\text{F}$ (-18 $^{\circ}\text{C} - 24 ^{\circ}\text{C}$).	

APPLICATION		
Thinning	Product should not be thinned.	
Primer	None normally required over approved substrates, but adhesion tests are recommended. For all Metal substrates and new TPO or PVC, a primer is required.	
Mixing Instructions	Mix before application to ensure uniform color and consistency. Power mixing is recommended. Do not use a paint shaker to mix.	
Application	Apply by brush, trowel or putty knife as received at a minimum wet thickness of 1/8" (3.2 mm) and spread at least 3" (76.2 mm) in all directions from the affected area for an approximate coverage rate of 12 ft² per Gal. For cold weather application, keep material stored above 65 °F (18 °C). Do not apply to substrates with temperatures below freezing or above 120 °F (49 °C).	
	GacoPatch Compliant may be applied to damp horizontal surfaces, but any standing water should first be removed.	
Dry Time	At ½" (3.2 mm) thick, in 75 °F (24 °C) temperatures and 55% relative humidity, GacoPatch Compliant will be tack-free in 4 hours, fully cured in 40 hours, but can be rained on within 60 minutes. Product is moisture cure; low humidity will result in longer cure times.	
Application of Top Coats	GacoPatch Compliant is UV stable. No top coat is required. Product is not intended to be painted or covered over with any product other than GacoFlex silicone roof coatings when applicable.	
Clean Up	Application tools and equipment can be cleaned with GacoFlex T5110 Compliant Solvent or 100% Pure Mineral Spirits. DO NOT USE WATER OR RECLAIMED SOLVENTS.	

For specific Safety and Health information, please refer to Safety Data Sheet.