



GacoFlex™

SF2036 WalkPad

A stay-put solution for creating highly-visible rooftop walkways.

COMPLETE IT!

To complete the walkway, apply GacoFlex WalkPad Granules, a custom color blend of quartz granules designed for use over GacoFlex WalkPad. Simply spread the granules on top of WalkPad while it is still wet, to provide traction and resistance to wear under pedestrian maintenance traffic.

GacoFlex WalkPad is a durable, silicone-based, solvent-free sealant that is combined with a reinforcing agent to provide durability and resistance to traffic and tears.

When applied on top of GacoFlex coatings and other roofing materials, GacoFlex WalkPad provides a walkway for pedestrian maintenance traffic and its yellow color provides high visibility.

GacoFlex Walkpad can be applied with a brush or trowel to make the process of creating a rooftop walkway surface fast and easy.



800 456 4226
gaco.com

GacoFlex SF2036 WalkPad

Solvent-free 100% silicone walkway system | November 2019

DESCRIPTION	GacoFlex SF2036 WalkPad is a silicone-based, solvent-free, single-component waterproof elastomeric moisture-curing sealant combined with a reinforcing agent and is specifically formulated for exceptional durability.	
USAGE	WalkPad is intended for application over GacoFlex Silicone Coatings and a variety of other roofing substrates to create a rooftop walkway for pedestrian maintenance traffic. Unlike conventional mats, WalkPad becomes an integral part of the roof. The yellow color provides a highly visible and aesthetic rooftop walkway, and when combined with GacoFlex WalkPad Granules will offer traction and resistance to wear under light foot traffic. GacoFlex WalkPad SF2036 is the only walk pad system approved for use with GacoFlex S20 Series and S2100 Coatings. WalkPad should not be used on SBS or Coated SBS roofing membranes.	
COLOR	Yellow	
APPLIED PRODUCT DATA		
WEATHERABILITY	Excellent durability, color stability and chalk resistance.	
TOXICITY	Not for use in contact with edible substances or potable water.	
ADHESION	Adhesion is excellent when applied directly over GacoFlex Silicone Coatings. A primer may be required for adhesion to other surfaces including built-up roofing, modified bitumen capsheet, single ply roofing (EPDM, TPO, PVC and Hypalon®), masonry, concrete, and wood. A primer must be used on all ferrous metals to prevent corrosion. Contact Gaco's Technical Department for specific recommendations.	
PRELIMINARY RESULTS BASED ON FILM THICKNESS OF 20 DRY MILS	Physical properties tests pending, in accordance with ASTM D6694 with a film thickness of 60 dry mils.	
TENSILE Initial Tensile Strength Elongation	ASTM D2370 306 ± 10 psi 130%	
TEAR RESISTANCE	ASTM D624 Die C	25 lbs per square inch
HARDNESS	ASTM D2240 Shore A	55
WATER VAPOR PERMEANCE	ASTM E96 Procedure B	7.0 perms
LOW TEMPERATURE FLEX	ASTM D522 Method B	Pass
PACKAGED PRODUCT DATA		
THEORETICAL COVERAGE	4 gallons per 100 sq. ft.NOTE: Actual coverage may be less due to surface profile, losses due to overspray and wind, and residual coating left in the container.	
SOLIDS	96% by Weight / 95% by Volume	
VOC	35 g/l	
FLASH POINT	ASTM D3278	178°F (81°C)
STORAGE STABILITY	Two years from date of manufacture when stored in sealed containers between 0°F - 80°F (-17°C - 26°C).	
APPLICATION		
MIXING	Mix before application to ensure uniform color and consistency.	
THINNING	Product is not intended to be thinned.	
PRIMER	No primer is needed when WalkPad is being applied directly over GacoFlex Silicone Coatings. If applying WalkPad to any other surface, apply GacoFlex E5320 2-Part Epoxy Primer/Filler according to label directions.	
APPLICATION	Apply by brush or trowel as received. For application utilizing equipment contact Gaco. For cold weather application, keep material stored above 65°F (18°C). Do not apply if rain is expected within 1 hour. For application in temperatures below freezing or above 120°F (49°C) contact Gaco. - Apply WalkPad at a rate of 4 gallons per 100 sq. ft. - When using WalkPad to create a rooftop walkway for pedestrian maintenance traffic, it is recommended that GacoFlex WalkPad Granules be applied to the wet product at a rate of 0.5 lb. per 100 sq.ft. to help ensure good traction. CAUTION: While the use of granules will improve traction, caution should still be exercised when walking on WalkPad, especially in wet conditions. NOTE: Application rate is job-specific. Additional material may be required due to surface profile, losses due to overspray and wind, and residual coating left in the container.	
DRY TIME	Allow to dry a minimum of 4 hours at 55°F (13°C) or higher, or until it can be safely walked on (product is moisture cure, low humidity will result in longer dry times).	
CLEAN UP	Clean up application tools and equipment with GacoFlex Silicone Solvent. DO NOT USE WATER OR RECLAIMED SOLVENTS.	
For specific Safety and Health information please refer to Material Safety Data Sheet.		

Gaco is a Firestone Building Products brand.

MKG1005 1119 © 2019 Firestone Building Products Company, LLC

gaco.com | 800 456 4226