



Application Specification:

RF-S20-30-15

Revised: 06/2021

**DIVISION 07 01 50.61:
GACOFLEX™ S20 SERIES SILICONE ELASTOMERIC ROOF COATING
AND GACOROOFFOAM™ OVER EXISTING SPRAYED-IN-PLACE
POLYURETHANE FOAM ROOFING**

PART 1 – GENERAL

1.1 SUMMARY

- A. This specification provides for the complete removal of the protective topcoat installed over an existing roof foam (via mechanical grinding/scarification), and for the installation of a new layer of sprayed-in-place polyurethane foam and silicone coating roofing system directly over the existing and properly prepared foam. Any areas of wet and/or damaged foam must be completely removed and replaced.

Surfaces to receive the roof covering system must comply with applicable building codes. Always check with local code authorities to determine whether a structure is eligible to receive an additional roof layer and perform full tear-offs where required.

The substrate must be inspected to ensure integrity and water tightness and all necessary repairs should be made before application of the new polyurethane foam and coating system is installed.

When properly applied, the GacoFlex S20 Series Silicone Roof Coating provides a weatherproof seal that protects the GacoRoofFoam from degradation caused by ultraviolet light, water, and other normal weathering hazards. This application incorporates the optional application of granules. The thickness of the foam can be varied to create a positive slope to improve drainage. The appearance of the system depends on the finished surface of the polyurethane foam which normally has slight undulations in thickness. Sprayed-in-place polyurethane foam mirrors the contour of the substrate and will reflect projections and depressions.

- B. The GacoFlex S20 Series Silicone Coating System discussed in this specification has a moderate rate of water vapor transmission. The GacoFlex S20 Series Coating System is not recommended for use on cold storage or cryogenic structures that may have constant high vapor drive causing long-term accumulation of moisture in the roofing system that serves as a substrate for the S20 Series Coating System. Consult Gaco for vapor retardant systems to use on refrigerated structures
- C. This specification is intended only as a guide for the development of a project specification. The suitability of this specification for a particular project must be determined by a qualified representative of the owner.

Conditions to check and corrections to consider are:

- The sprayed-in-place polyurethane foam roofing substrate must be well adhered and intact.
- The sprayed-in-place polyurethane foam roofing substrate must not be wet.
- The structural decking must be sound.

Elements of this specification may require modification in order to clearly delineate project requirements. Sections that are not pertinent may be deleted.

1.2 RELATED SECTIONS

A. Cast-In-Place Concrete:	Division 03 30 00	F. Vapor /Air Barriers:	Division 07 25 00
B. Flashing/Sheet Metal:	Division 07 60 00	G. Board Insulation:	Division 07 22 00
C. Roof Accessories:	Division 07 72 00	H. Skylights:	Division 08 60 00
D. Rough Carpentry/Wood Blocking:	Division 06 10 00	I. Metal Decking:	Division 05 30 00
E. Drains, Vents and Penetrations:	Division 07 72 00		

1.3 SUBMITTALS

- A. **PRODUCT DATA:**
Submit manufacturer's standard submittal package including specification, installation instructions and general information for each waterproofing material.
- B. **APPLICATOR QUALIFICATIONS:**
Submit current Letter of Good Standing from the specified waterproofing manufacturer.
- C. **SAMPLE:**
Two physical samples reflecting the completed installation, i.e. finish, color, must be submitted to the owner / owner's representative. Size of these samples shall be 12 in x 12 in (304.8 mm x 304.8 mm) minimum.
- D. **SUBSTRATE CONDITIONS:**
1. Applicator to present to owner a completed inspection form verifying substrate condition and any noted defects not specifically addressed in regard to the installation of the coating.
 2. Surface shall be free from loose dirt, stone, debris, moisture, and shall be in stable condition. Any work on the area to receive this application shall be completed prior to the installation of the coating.
 3. Applicator shall complete a substrate inspection prior to the start of the installation of the coating. The architect/owner and applicator shall accept the substrate. Start of the work constitutes acceptance.

1.4 QUALIFICATIONS

- A. Primary waterproofing materials shall be the products of a single manufacturer. Secondary materials shall be recommended by the primary manufacturer. The manufacturer shall have a minimum of ten (10) years' experience in the manufacture of materials of this type.
- B. Applicators shall have a minimum of five (5) years' experience in the application of waterproofing materials of the type specified. The Applicator shall possess a current Letter of Good Standing from the specified waterproofing manufacturer.
- C. **PRE-BID CONFERENCE:**
Ten (10) working days prior to the bid opening there is to be a mandatory Pre-Bid Conference. Those not attending the Pre-Bid Conference will not be allowed to bid the project. All products considered an equal to the specified product or any changes in the scope of work, installation, or specifications must be presented at the Pre-Bid Conference. If a change in the specifications is accepted, it will be considered as an alternate and will be presented as a bid addendum issued five (5) working days prior to the bid opening. No other changes to the specification or bid documents will be accepted.
- D. Materials other than those specified shall be submitted to the architect/owner for approval no later than ten (10) days prior to the bid date. In requesting prior approval, it shall be necessary to submit:
1. A letter of certification, signed by an officer of the manufacturer, stating that the alternate material is equal to or better than the specified product.
 2. Independent laboratory test data giving physical property values in comparison to the specified material.
- E. **PRE-INSTALLATION CONFERENCE:**
Just prior to the commencement of the installation, meet at the jobsite with a representative of the coating manufacturer, Applicator, general contractor, architect, and other parties affected by this section. Review the methods and procedures, substrate conditions, scheduling, and safety.

1.5 DELIVERY, STORAGE AND HANDLING

- A. Deliver all materials in sufficient quantities as not to cause delays in the application of the roofing system. Owner/owner's representative shall reject damaged materials not conforming. Rejected materials shall be removed immediately from the job site and replaced at no additional cost to the owner.
- B. Store materials as recommended by the manufacturer and conforming to applicable safety regulatory agencies: town, state, and federal. Refer to all applicable data including, but not limited to Safety Data Sheets, Product Data Sheets, product labels, and specific instructions for personal protection.

- C. Provide adequate ventilation, protection from hazardous fumes, overspray potential to workers, and associated trades in close proximity of the application.

1.6 ENVIRONMENTAL REQUIREMENTS

- A. Proceed with the work of this section only when the existing and forecasted weather conditions will permit the application to be performed in accordance with the manufacturer's recommendations. **Do not** install polyurethane foam under the following conditions:
 - 1. When the surface temperature is below 50 °F (10 °C) or is above 160 °F (71 °C).
 - 2. When the relative humidity is above 80% or temperature is within 5 °F (2.8 °C) of the dew point.
 - 3. When the wind velocity exceeds 15 mph (24 kph)
(Without the use of a wind screen)

1.7 WARRANTY

- A. Manufacturer warrants that the material supplied will meet or exceed physical properties as published. The Applicator guarantees that workmanship will be free of defects in coating application. Since performance of previously applied coatings is beyond the control of Manufacturer and Applicator, requests for additional warranty coverage shall be subject to prior approval by Manufacturer.
- B. **A FIFTEEN (15) YEAR LABOR AND MATERIAL WARRANTY MUST BE OBTAINED THROUGH THE MANUFACTURER.**
- C. **PROTECTION OF BUILDING AND OCCUPANTS:**
 - 1. All surfaces not to receive the coating specified shall be protected from overspray hazard, e.g., windows, doors, exterior surfaces and facades, parking lots, and vehicles. Protective coverings shall be secured against wind and shall be vented if used in conjunction with applications preventing collection and moisture.
 - 2. Applicator to post signs noting potential overspray hazard within 400 ft (121.90 m) of applications.
 - 3. All air intake ventilation equipment shall be turned off to prevent fumes from entering building.
 - 4. Surfaces damaged during application shall be restored at no expense to the owner.
 - 5. No smoking signs to be posted as mandated by local fire officials.
- D. **SUBSTRATE:**
Proceed with work as specified only after substrate construction, preparation, and detail work has been completed.
- E. **EQUIPMENT:**
All equipment used during operations shall be located so as not to adversely affect the daily operations or endanger occupants, structure, or materials on-site. All spray equipment must be grounded during operations.

PART 2 - PRODUCTS

2.1 MANUFACTURER

Acceptable Manufacturers:
Gaco, www.gaco.com

2.2 MATERIALS

- A. **CLEANER:**
GacoFlex GacoWash Concentrated Cleaner
- B. **PRIMER:**
GacoFlex A4121 Water-Borne Acrylic Primer
GacoFlex E5320 2-Part Epoxy Primer/Filler *As required where the roofing substrate is rusted

C. FLASHING:

GacoFlex GacoFlashFoam
 GacoFlex NF621 Neoprene Sheet Flashing 1/16 in (1.6 mm)**
 GacoFlex N1207 VOC-Compliant General-Purpose Adhesive **
 **As required for dynamically moving joints

D. EXPANSION JOINT COVERS:

GacoFlex NF621 Neoprene Sheet, 1/16 in (1.6 mm) thick
 GacoFlex N1207 VOC-Compliant General-Purpose Adhesive

E. POLYURETHANE FOAM:

Shall be designed for a spray application resulting in high-quality, rigid polyurethane under the prevailing application conditions.

A SINGLE PRODUCT SHALL BE SELECTED FROM THE TWO (2) OPTIONS LISTED IN THIS SECTION, of the proper formulation to meet climatic conditions at the time of the application, manufactured by Gaco meeting minimum physical and performance properties as specified.

1. OPTION #1:

GacoRoofFoam Low GWP Spray-In-Place Polyurethane Foam having the following minimum physical and performance properties:

GacoRoofFoam Low GWP Spray-In-Place Polyurethane Foam		
PROPERTY	VALUE	TEST METHOD
NOMINAL DENSITY	2.7 - 3.4 lbs / ft ³ (43.2 – 54.5 kg / m ³)	ASTM D1622-93
CLOSED CELLS	94.3%	ASTM D2856 C94
COMPRESSIVE	50 psi (0.34 MPa)	ASTM D1621
INITIAL R-VALUE	6.4 (1.13 RSI)	ASTM C518

OR

2. OPTION #2:

GacoRoofFoam F2733 Spray-In-Place Polyurethane Foam having the following minimum physical and performance properties

GacoRoofFoam F2733 Spray-In-Place Polyurethane Foam		
PROPERTY	VALUE	TEST METHOD
NOMINAL DENSITY	2.5 - 3.0 lbs / ft ³ (40 - 48 kg / m ³)	ASTM D1622-93
CLOSED CELLS	94.3%	ASTM D2856 C94
COMPRESSIVE	50.1 psi (0.34 bar)	ASTM D1621
INITIAL R-VALUE	6.5 (1.15 RSI)	ASTM C518

NOTE: It is Gaco's position that the use of foamed plastic insulation for interior application on walls or ceilings may represent an unreasonable fire hazard unless the foamed plastic insulation is covered with a thermal barrier and the resulting composite construction has a minimum fifteen (15) minute rating as listed by Factory Mutual Research Corporation or other equally accepted listing agency.

Fire rated coating systems for plastic foam insulation tested under ASTM E108 Class "A" Roof Composite Construction do not qualify for thermal barrier use on interior walls and ceilings.

F. SILICONE COATING:

Meets the following minimum physical and performance properties:

GacoFlex S20 Series Silicone Elastomeric Roof Coating		
PROPERTY	VALUE	TEST METHOD
TENSILE STRENGTH @ 73 °F (23 °C)	450 psi (3.1 MPa)	ASTM D412
ELONGATION AT BREAK @ 73 °F (23 °C)	174 %	ASTM D412
TENSILE STRENGTH @ 0 °F (-18 °C)	574 psi (3.9 MPa)	ASTM D412
ELONGATION AT BREAK @ 0 °F (-18 °C)	169 %	ASTM D412
SOLIDS	Weight: 96.5 % Volume: 95 %	Method 404 Fed. Std. 141
VOC	37 g / L (0.08 lb / 0.26 gal)	EPA Method 24
REFLECTANCE (INITIAL)	Initial: 0.874 After Soiling: 0.812	ASTM C1549 S2000 White
SRI	Initial: 110 After Soiling: 101	ASTM E1980 S2000 White
WATER VAPOR PERMEABILITY	5.0 perm in	ASTM E96

PART 3 - EXECUTION**3.1 EXAMINATION**

- A. A nuclear or infrared scan must be performed to identify any moisture trapped in the existing roof system. Scans must be provided to Product Manufacturer with the Pre-Installation Notice prior to the commencement of work.
- B. Repairs to structural components supporting the roof should be completed.
- C. All associated construction (e.g., drain installation, edge flashing, penetrations and mechanical apparatus) shall be completed prior to the commencement of the specified roof foam and coating system.
- D. Verify that all other work involved with this area, done under other sections, has been completed and accepted by the architect and general contractor prior to starting the waterproofing application.

NOTE: Polyurethane foam roofs with cementitious coatings may not be suitable substrates for "Re-Foam" applications. Contact Technical Services for recommendations.

3.2 PREPARATION**NOTE: IT IS EXTREMELY IMPORTANT FOR THE ROOF TO BE CLEAN AND DRY**

- A. Mask off all adjoining areas that will not receive the roofing system.
- B. Any areas of wet foam must be removed down to the underlying substrate and new GacoRoofFoam installed to match the height of the existing foam.
- C. Scarification: Scarify the coated roof surface with a mechanical grinder to fully expose the existing Polyurethane Foam. Remove particulate residue using brooms, hand blowers and industrial vacuum. It imperative that the exposed foam be clean, dry and sound. Only expose as much foam as can be cleaned and primed prior to the completion of work each day

3.3 INSTALLATION**A. TECHNICAL ADVICE:**

The installation of this system shall be accomplished with the advice of, the manufacturer's technical representative. Contact Technical Services for assistance.

NOTE: Surface should be clean and dry, remove all oils and other surface contaminants.

B. PRIMER:**STEP 1:**

To the exposed foam, apply GacoFlex A4121 Water-Borne Acrylic Primer at an approximate rate of 1.0 gal / 250 ft² (3.8 L / 23 m²) until the GacoRoofFoam can be installed. GacoFlex A4121 Primer may be exposed a maximum of five (5) days prior to being covered with GacoRoofFoam. Primer must be completely dry before moving to the next step of installation.

NOTE: In the event that the A4121 Primer is exposed longer than five (5) days, contact Technical Services for assistance – do not proceed to next step.

STEP 2:

FOR STEEL, ALUMINUM, COPPER AND FERROUS METALS: Apply GacoFlex E5320 2-Part Epoxy Primer/Filler at an approximate rate of 1.0 gal / 300 ft² (3.8 L / 28 m²). The primer must be completely dry before starting the polyurethane foam application.

C. FLASHING:

GacoFlashFoam is self-flashing and can be used at curbs, parapets, walls and penetrations. Flashing at dynamically moving joints require GacoFlex NF621 Neoprene Sheet Flashing 1/16 in (1.6 mm) and VOC-Compliant General-Purpose Adhesive Contact a Gaco Representative for assistance and refer to product documentation available at Gaco.com for specific directions.

D. EXPANSION JOINTS:

Where called for, expansion joint covers will be GacoFlex NF621 Neoprene Sheet, 1/16 in (1.6 mm) thick, using GacoFlex N1207 VOC Compliant General-Purpose Adhesive, in a width of "_____" (TO BE STATED IN THE PUBLISHED SPECIFICATION. IF THERE IS NONE STATED, THE BIDS WILL BE BASED ON 12 IN (304.8 MM)).

E. SPRAYED-IN-PLACE POLYURETHANE FOAM:

As determined in "SECTION 2.2 MATERIALS – E. SPRAY-IN-PLACE POLYURETHANE FOAM" of this document, apply selected product at a thickness of 1.0 in (25 mm) ± 0.25 in (6 mm). Neatly terminate the sprayed-in-place polyurethane foam on all vertical surfaces, (e.g., pipe penetrations, vents, mechanical equipment, parapet walls, etc.) a minimum of 3 in (76 mm) or 2¹/₂ times as specified minimum foam thickness.

Example: If 1 in (25 mm) minimum is specified, all vertical terminations shall have a minimum of 2.5 in (64 mm) sprayed up onto the vertical surface and canted to the horizontal surface.

THE FOLLOWING APPLICATION QUALITIES SHALL BE SATISFIED:

1. The polyurethane foam spray application shall be limited to an area which can be completed to full foam thickness in one day.
2. The completed polyurethane foam surface shall be smooth to an orange peel texture; a popcorn texture is not acceptable.
3. The completed polyurethane foam surface shall be free of pinholes and "glass windows" due to improper equipment calibration or climatic conditions.
4. Apply the protective coating to the polyurethane foam surface on the same day of application.

F. SILICONE COATING:

Apply one coat of GacoFlex S20 Series Silicone Roof Coating at an average rate of 2 gal / 100 ft² (7.6 L / 9.3 m²) to obtain 32 mil Wet Film Thickness (WFT) / 30 mil Dry Film Thickness (DFT). Double coat flashings and edge terminations

G. GRANULAR COAT (OPTIONAL):

An additional granular coat may be added. Apply one coat of GacoFlex S20 Series Silicone Roof Coating at the rate of not less than 0.5 gal / 100 ft² (1.9 L / 9.3 m²) to obtain 24 mil Wet Film Thickness (WFT) / 22 mil Dry Film Thickness (DFT).

IMMEDIATELY broadcast roofing granules into the finish coat at the rate of 30 lbs / 100 ft². (13.6 kg / 9.3 m²).

H. WALKPAD (OPTIONAL):

Apply one coat of GacoFlex SF2036 WalkPad at a rate of 4 gal / 100 ft² (15.1 L / 9.3 m²) to obtain 24 mil Wet Film Thickness (WFT). Broadcast GacoWalkPad safety yellow granules into wet coating at a rate of 0.5 lbs / 100 ft² to ensure good traction.

NOTE: GacoFlex SF4236 WalkPad is acceptable substitute for GacoFlex SF2036 WalkPad.

NOTE: Tape off area to receive the GacoWalkPad area using duct tape. After application remove duct tape while coating is still wet.

NOTE: GacoFlex SF2036 and SF4236 WalkPad are the *only* walk pad systems approved for inclusion in this Specification.

CAUTION: *While the use of granules will improve traction, caution should still be exercised when walking on the coated roofing system, especially in wet conditions.*

3.4 FIELD QUALITY CONTROL

- A. The Applicator shall maintain the system to verify compliance with this specification.
 - 1. Thickness of polyurethane foam and applied coating shall be measured and recorded for each coat and the total protective coating system.
- B. The owner's representative has the option of taking core samples to verify compliance with the specification.
 - 1. Cut out sections shall be immediately repaired by the applicator at its expense.
 - 2. All costs of testing the core samples shall be paid for by the owner.
- C. Any variations from the specified limits found by the applicator or owner's representative shall be corrected by the Applicator.
- D. **MINIMUM DRY FILM THICKNESS (DFT) REQUIREMENT:**

Gaco recommends adding a 10% variance factor to obtain the minimum DFT mil thickness required. It is the Applicator's responsibility to calculate the amount of coating needed to obtain the minimum DFT mil thickness required.
- E. No traffic shall be permitted on the completed surface for a minimum of three (3) days. Damage to the surface by other trades shall not be the responsibility of the Applicator.